

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 62-054710

(43) Date of publication of application : 10.03.1987

(51) Int. Cl.

C08F220/36  
// C09D 3/80

(21)Application number : 60-195038

(71)Applicant : KURARAY CO LTD

(22)Date of filing : 03.09.1985


(72)Inventor : FURUMIYA YUKIATSU  
HIRAI KOJI

**(54) URETHANE-MODIFIED ACRYLATE COMPOSITION**

**(57)Abstract:**

**PURPOSE:** To obtain the titled composition excellent in flexibility, film properties, waterproofness, weathering resistance, etc., and suitable as, e.g., a binder of paints or magnetic tapes, by mixing a urethane-modified acrylate of a specified structure with a polymerizable monomer.

**CONSTITUTION:** The purpose urethane-modified acrylate composition is obtained by mixing a urethane-modified acrylate (A) of formula I (wherein R<sup>1</sup> and R<sup>1'</sup> are each H or methyl, R<sup>2</sup> and R<sup>2'</sup> are each a polyalcohol, R<sup>3</sup> is an organic diisocyanate, R<sup>4</sup> is a polyester polyol having groups of formulas II and III as structural components, m is 1W5 and l and n are each 1W3) with a polymerizable monomer (B) (e.g., styrene or methyl methacrylate). Component A is produced by using a polyester polyol, an organic diisocyanate (e.g., tolylene diisocyanate) and a hydroxyl group-containing (meth)acrylate (e.g., 2-hydroxyethyl acrylate) as starting materials.



## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

**[Date of extinction of right]**

Copyright (C); 1998,2003 Japan Patent Office